

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B27K 3/00, 5/00	A1	(11) International Publication Number: WO 99/15321 (43) International Publication Date: 1 April 1999 (01.04.99)
(21) International Application Number: PCT/IB97/01130 (22) International Filing Date: 19 September 1997 (19.09.97) (71) Applicants (for all designated States except US): LIGNOCELL HOLZ-BIOTECHNOLOGIE GESELLSCHAFT MBH [AT/AT]; Industriestrasse West 5, A-8605 Kapfenberg (AT). UNIVERSITY OF ABERTAY [GB/GB]; Bell Street, Dundee DD1 1HG (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): MESSNER, Kurt [AT/AT]; Neuwaldeggerstrasse 16/3/7, A-1170 Wien (AT). FLECK, Vinzenz [AT/AT]; Antonienhöhe 36, A-8130 Frohnleiten (AT). BRUCE, Alan [GB/GB]; Siwt, University of Abertay, Bell Street, Dundee DD1 1HG (GB). ROSNER, Bernhard [AT/AT]; Roseggergasse 47/6, A-1160 Wien (AT). (74) Common Representative: MESSNER, Kurt; Neuwaldeggerstrasse 16/3/7, A-1170 Wien (AT).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESS FOR IMPROVING THE IMPREGNABILITY OF WOOD BY PRETREATMENT WITH FUNGI (57) Abstract The object of the invention is a method for improving the impregnability of refractory wood species by pretreatment with fungi of the genera <i>Trichoderma</i> or <i>Gliocladium</i> or with weakly wood-degrading fungi. The pretreatment comprises a thermal treatment of the wood, the addition of a nutrient medium as well as an incubation phase to promote fungal growth. The incubation phase is stopped when the desired depth of penetration of the fungus is reached. The wood is subsequently impregnated with a wood impregnating agent. The typical result of the fungal pretreatment is an increase in the depth of penetration of the impregnating agent to a depth of penetration of 5 mm to 30 mm required depending on the intended use.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

PROCESS FOR IMPROVING THE IMPREGNABILITY OF WOOD BY PRETREATMENT WITH FUNGI

5

Technical field:

The invention describes a method for improving the impregnability of wood. Various wood species, such as spruce, Douglas fir, fir, oak or acacia, are characterized by favourable properties, such as resistance to checking and splitting as well as low distortion and torsion, straight fibers and minimal branching. These wood species are not widely used because they are difficult to impregnate with chemicals. This is generally true of the heart wood of all wood species. Even if the most efficient impregnating methods are used in wood protection, a wood preservative frequently does not penetrate deeper than 2-3 mm, while the standards in wood protection for timber in European hazard class IV (Ground Contact Timbers) call for a depth of penetration of at least 5-10 mm and of 6 - 30 mm for poles. For example an uptake of at least 63 kg of creosote/m³ of wood is required for palisades and of 90 kg/m³ for poles (figure for U.K. is 115Kg/m³). This limit cannot be reached with the above-mentioned refractory wood species without additional pretreatment.

At present the method of pretreatment most frequently used in wood protection is the very costly incising method according to which 3 cm deep holes spaced 4 - 8 mm apart are cut into the base of the pole or throughout the sawn timber member in order to promote the penetration of the wood preservative.

The reason for the poor impregnability is the behaviour of the pits during wood drying. Pits are connective openings between the wood cells which permit water transport. The anatomy of the pits is such that the two cell walls on either side of the middle lamella form a dome-

shaped cavity and each has an opening called a pore. At this point the middle lamella is thickened to form the so-called torus. When the wood is dried, this thickened portion
5 attaches to the border of the pore and seals it irreversibly in refractory wood species. The chemical background of this process has not been ascertained yet.

Background Art:

- 10 At present the most common method of improving the impregnability of wood by wood preservatives is the wet storage of wood in ponds for a period of several months, which promotes the development of bacterial populations that open the pits. However, this process cannot be controlled and leads to irregular results.
- 15 A more modern version of this method was developed for the pretreatment of pulpwood in which a mixture of selected strains of bacteria is used and which is said to result in a reduction of blue stain and resin degradation as well as reduction of the cooking time (WO 9636765). A similar effect is achieved in pulping also by pretreating wood chips with the fungus *Ophiostoma piliferum* (Blanchette, Farrell and Burnes 1992, Tappi 75, 102-
20 106).

In wood protection attempts have been made to restore the pit passage by the action of a pectinolytic enzyme preparation (German Patent DD 292 864 A5). The disadvantage of these processes is that they are designed to degrade only one particular component of
25 the pits, such as pectin, however apparently several components, not yet determined, are responsible for the pit closure.

Disclosure of the invention:

The subject of the invention is a biological process in which the impregnability of the wood
5 by wood preservatives is improved by growing fungi on the wood. Preferably fungi of the
genus

Trichoderma, such as Trichoderma viride SIWT T70, Trichoderma aureoviride SIWT T1 or
the strains Trichoderma harzianum LC1, LC2, Hypocrea piluliferum LC3, or Gliocladium
10 roseum LC4 as well as weakly wood-degrading fungi, such as Phanerochaete
chrysosporium LC5 or Dichomitus squalens LC6 are employed. In the latter case these
fungi are eradicated after incubation.

The use of living wood-colonizing fungi has the advantage over the use of enzyme
15 solutions in that enzyme solutions have to be applied by a separate impregnating
process, which poses a problem in particular with refractory wood species, whereas fungi
may actively grow into the wood with the help of their filamentous hyphae. Another
advantage of fungi is that they excrete the necessary mixture of enzymes and other low
molecular size agents in the vicinity of the pits, which is required for the opening of the pit
20 passages, but the composition of which has not been determined yet.

The inventive feature of the present process is that for improving the impregnability of
wood it is inoculated with selected strains of fungi of the genus Trichoderma or
Gliocladium, or with strains selected from the group of weakly wood-degrading fungi
25 which are particularly suited to improve the uptake of the impregnating agent by the
wood. Use of selected strains of Trichoderma or Gliocladium cause no decrease in
strength of the timber and additionally have the effect of biological wood protection, for
example Trichoderma harzianum LC1, LC2, Hypocrea piluliferum LC3 (EP 0 615 409 B1).
The use of weakly wood-degrading fungi only results in limited damage to the wood
30 during the period of treatment (usually below 10% strength loss).

According to the invention the weakly wood-degrading fungi are eradicated after pretreatment as soon as the desired impregnating aim is achieved to avoid extended
5 damage to the wood.

The decontaminating and growth promoting measures prior to inoculation enable the applied strains of fungi to rapidly grow into the wood without any appreciable competition by other organisms and to perform their pit opening activity there. The process makes it
10 possible to use also wood species which are difficult to impregnate without expensive and time consuming mechanical pretreatment processes, such as the incising method, in the same fields of application as easily impregnable wood species thereby significantly expanding the market for such species.

15 Best mode for carrying out the invention:

The method includes a decontamination stage prior to the application of the biological agent to the timber. This stage may not be required however dependant on the timing of the treatment after felling of the timber. A principle of the method according to the
20 invention is to promote the fungal growth preferably (though not essentially) by thermal decontamination of the wood surface prior to inoculation and by the addition of a growth promoting medium. The decontamination of the wood surface is effected preferably by steam at 100-120°C for 10 seconds - 30 minutes, depending on the degree of contamination, followed by a cooling phase. The growth promoting medium may be
25 applied separately or jointly with the fungal inoculum. It contains preferably a diluted suspension of cornsteep liquor.

According to the invention inoculation is effected in the case of sporulating fungi, such as the *Trichoderma* and *Gliocladium* species, by applying a spore suspension, and in the case of non-sporulating fungi, such as basidiomycetes, by applying a mycelium suspension to the wood surface. The inoculating suspension may be applied by spraying, dipping, brushing, etc., the inoculum concentration should exceed 100 colony-forming units / ml.

The incubating phase ideally takes place at the optimum temperature of the respective fungus employed and ranges from 10 to 50°C, but preferably from 20 to 30°C. It may be stopped as soon as the desired depth of penetration of the fungus and the resulting opening of the pits is reached. This objective is reached - depending on the strain of fungus - after a few days to 4 weeks at the most. The resulting loss of wood strength ranges from 0% for *Trichoderma* or *Gliocladium* species to no more than 10% for weakly degrading basidiomycetes depending on the fungal strain (see results table).

If weakly wood-degrading fungi are used, the fungus grown into the wood is eradicated according to the invention at the end of incubation. This may be done, depending on the type of method used, either in the course of wood drying in drying kilns at elevated temperatures of 40-100°C or by steaming of the wood at 100-120°C or by a fungicide applied after fungal colonisation. Furthermore, the fungus may be eradicated in the course of pressure treatment in which temperatures of up to 160°C are reached.

The subsequent impregnating process may be a pressure treatment (high pressure or low pressure process), non-pressure treatment (dip treatment), or special process. The impregnating agents to be employed are not limited to wood preservatives, but comprise all chemical substances designed for impregnation, such as fire protectants, synthetic resins, and chemicals designed for wood modification etc.

Example:

Spruce logs stripped of the bark (*Picea abies*, 1 m length, 100 to 200% wood moisture content) were subjected to a decontamination treatment by steaming for 10 minutes and
5 were subsequently cooled down to ambient temperature.

The inoculum fungi *Trichoderma viride* SIWT T70, *Trichoderma aureoviride* SIWT T1, *Trichoderma harzianum* LC1, *Trichoderma harzianum* LC2, *Trichoderma harzianum* LC3, *Gliocladium roseum* LC4, *Phanerochaete chrysosporium* LC5 *Dichomitus squalens* LC6,
10 were grown in Petri dishes on 2% malt agar and blended in a sterile mixer in a 2% solution of cornsteep liquor. The concentrated fungal suspensions were diluted in a growth promoting medium containing cornsteep liquor and were used as an inoculum. Inoculation was effected by dipping 10 spruce logs into the microbial inoculum of each test fungus in the respective mycelium suspension. The strains were subsequently
15 incubated in rooms with constant climate at the optimum temperatures for each test fungus for 1, 2, 3 or 4 weeks, respectively.

After the incubation period the spruce logs were dried in a drying kiln at temperatures between 50 and 65°C for a period of 12 days to 10 - 20 % wood moisture content. Ten
20 logs not inoculated with fungi were dried under the same conditions to serve as controls.

The pretreated logs and the controls were impregnated with creosote in the same way according to an industrial pressure treatment process designed for pine wood. They were subsequently cut apart and the depth of penetration measured. Additionally test wood
25 blocks were cut out and subjected to strength tests (ISO Standard No.3349) as well as analyzed for the loading of the wood preservative.

Results:

		weeks of incubation	depth of penetration (cm)	creosote loading kg/m ³	strength loss (%)
5	SIWT T70	3	2,7 - 3,0	150	0
10	SIWT T1	3	2,0 - 2,7	160	0
	T. harz. LC1	3	2,5 - 2,9	160	0
	T. harz. LC2	3	2,0 - 2,7	155	0
15	H. pil. LC3	3	2,6 - 3,0	160	0
	Gl. ros. LC4	3	2,1 - 2,9	160	0
20	Ph. chr. LC5	1	2,3 - 3,0	240	0
		2	2,3 - 3,2	260	10
		3	2,5 - 3,2	260	10
	D. squ. LC6	1	1,0 - 1,5	130	0
25		2	2,3 - 2,8	150	10 - 15
		3	2,3 - 3,0	250	10 - 15
	Controls		0,15 - 0,95 *)		0

30

*) cannot be tested because penetration is not deep enough.

A depth of penetration of 2 - 3 cm correlates with a total penetration of the sap wood area of the logs with creosote.

35

Industrial Applicability:

The method according to the invention is applicable in all those areas in which the capability of certain wood species to take up any impregnating agent does not guarantee a particular quantity of uptake or depth of penetration. The main field of application is wood protection, as e.g. when using spruce wood (*Picea* spp.) for poles or palisades. Without any prior opening of the pit passages and clearing of blockage materials in the

40

ray parenchyma tissues the uptake of the wood preservatives required for protection of timber in soil contact situations can only be reached by very costly conventional physical processes. Preservative treatment levels required to meet national standards can however be achieved by the pretreatment according to the invention. Similarly, sawn construction timbers can be more properly treated with preservatives using the method.

However, the invention also extends to the impregnation of wood with other impregnating agents, such as synthetic resins, or to agents for the chemical modification of wood.

Applicant's or agent's file reference number	International application No. PCT/IB 97/01130
--	---

INDICATIONS RELATING TO A DEPOSITED MICROORGANISM

(PCT Rule 136is)

A. The indications made below relate to the microorganism referred to in the description on page <u>3/7/11</u> , line <u>8, 9, 10, 11, 28/2-26/10, 13, 14, 17, 20, 26</u>	
B. IDENTIFICATION OF DEPOSIT	
Further deposits are identified on an additional sheet <input type="checkbox"/>	
Name of depositary institution Centraalbureau voor Schimmelcultures	
Address of depositary institution (including postal code and country) CBS P.O. Box 273 NL 3740 AG BAARN	
Date of deposit 1) SEPT. 4, 1997 2) SEPT. 4, 1997 3) SEPT. 17, 1997 4) SEPT. 17, 1997 5) SEPT. 16, 1997	Accession Number 1) CBS 100063 2) CBS 100064 3) CBS 100071 2) CBS 100072 3) CBS 100073
C. ADDITIONAL INDICATIONS (leave blank if not applicable)	
This information is continued on an additional sheet <input type="checkbox"/>	
1) TRICHODERMA AUREOVIRIDE SIWT T1 2) TRICHODERMA VIRIDE SIWT T70 3) GLIOCLADIUM ROSEUM LC4 4) PHANEROCHAETE CHRYSOSPORIUM LC5 5) DICHOMITUS SQUALENS LCB	
D. DESIGNATED STATES FOR WHICH INDICATIONS ARE MADE (if the indications are not for all designated States)	
E. SEPARATE FURNISHING OF INDICATIONS (leave blank if not applicable)	
The indications listed below will be submitted to the International Bureau later (specify the general nature of the indications e.g., "Accession Number of Deposit")	
For receiving Office use only	For International Bureau use only
<input checked="" type="checkbox"/> This sheet was received with the international application	<input type="checkbox"/> This sheet was received by the International Bureau on:
Authorized officer <u>Agnes Wittmann-Regis</u>	Authorized officer

Applicant's or agent's file reference number	International application No. PCT/IB 97/01130
--	---

INDICATIONS RELATING TO A DEPOSITED MICROORGANISM

(PCT Rule 13bis)

A. The indications made below relate to the microorganism referred to in the description on page <u>3/7/11</u> , line <u>89, 101, 28/3-26/40, 13, 14, 17, 20, 26</u>	
B. IDENTIFICATION OF DEPOSIT	
Further deposits are identified on an additional sheet <input type="checkbox"/>	
Name of depositary institution Centraalbureau voor Schimmelcultures	
Address of depositary institution (including postal code and country) CBS P.O. Box 273 NL 3740 AG BAARN	
Date of deposit <u>1), 2), 3) Nov. 4, 1991</u>	Accession Number <u>1) CBS 595.91</u> <u>2) CBS 596.91 3) 597.91</u>
C. ADDITIONAL INDICATIONS (leave blank if not applicable)	
This information is continued on an additional sheet <input type="checkbox"/>	
1) TRICHODERMA HARZIANUM LC 1 2) TRICHODERMA HARZIANUM LC 2 3) HYPOCREA PILULIFERA LC 3	
D. DESIGNATED STATES FOR WHICH INDICATIONS ARE MADE (if the indications are not for all designated States)	
E. SEPARATE FURNISHING OF INDICATIONS (leave blank if not applicable)	
The indications listed below will be submitted to the International Bureau later (specify the general nature of the indications e.g., "Accession Number of Deposit")	
For receiving Office use only	For International Bureau use only
<input checked="" type="checkbox"/> This sheet was received with the international application	<input type="checkbox"/> This sheet was received by the International Bureau on:
Authorized officer <u>Agnes Wittmann-Regis</u>	Authorized officer

Claims:

1. A method for improving the impregnability of wood, characterized in that the wood to
5 be impregnated with any chemical is made accessible by fungal inoculation comprising
colonizing it with a fungus or a mixture of fungi or a mixture of fungi and other
microorganisms.
2. The method of claim 1, characterized in that the fungi used are selected from the
10 genus *Trichoderma* or its teleomorphic states like *Hypocrea*.
3. The method according to claims 1 and 2, characterized in that the fungi used are the
strains *Trichoderma viride* SIWT T70, *Trichoderma aureoviride* SIWT T1, *Trichoderma*
harzianum LC 1, *Trichoderma harzianum* LC 2, *Hypocrea piluliferum* LC 3.
15
4. The method according to claim 1, characterized in that the fungi used are selected
from the genus *Gliocladium*.
5. The method according to claims 1 and 4, characterized in that the fungus used is the
20 strain *Gliocladium roseum* LC4.
6. The method according to claim 1, characterized in that the fungi used are weakly
wood-degrading Basidiomycetes, Ascomycetes or Deuteromycetes.
- 25 7. The method according to claims 1 and 6, characterized in that the fungus used are the
strains *Phanerochaete chrysosporium* LC5 and *Dichomitus squalens* LC6.

8. The method according to one of claims 1 to 7, characterized in that the wood is
5 subjected to a chemical or thermal pretreatment for decontamination prior to fungal
inoculation, preferably with steam at a temperature of from 100-120°C, and is
subsequently cooled.
9. The method according to one of claims 1 to 8, characterized in that the wood to be
10 colonized by the fungus is supplied with a growth promoting medium, preferably
containing cornsteep liquor.
10. The method according to one of claims 1 to 9, characterized in that after fungal
inoculation an incubation phase adapted to the fungi used takes place, the incubating
15 temperature being from 10 to 50°C, preferably from 20 to 30°C.
11. The method according to one of claims 6 to 10, characterized in that the fungus is
eradicated after colonizing the wood, preferably by heat.
- 20 12. Any wooden member treated according to the method according to one of claims.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB 97/01130

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B27K3/00 B27K5/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B27K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 2 705 607 A (DEPTOS SA TONNELLERIE) 2 December 1994 see page 40, line 20-28 ----	1-12
A	EP 0 001 540 A (ENFORS SVEN OLOF ; MOLIN NILS (SE); MONTELIN EUGEN (SE)) 18 April 1979 see page 4, line 18-25; claim 1 ----	1
A	WO 93 08694 A (LIGNOCELL HOLZ BIOTECH) 13 May 1993 cited in the application see the whole document ----	1-12
A	GB 2 239 800 A (DUNDEE INST OF TECHNOLOGY ; QUARMBY ARTHUR (GB)) 17 July 1991 see claims ----- -/-	1-3, 12

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

*** Special categories of cited documents :**

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

8 July 1998

Date of mailing of the international search report

27/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Dalkafouki, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 97/01130

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 486 969 A (NILSSON THOMAS ET AL) 30 December 1969 see claims ---	1,4,12
A	DD 292 864 A (WEB WISS TC.HOLZ) 18 April 1991 cited in the application -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 97/01130

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
FR 2705607	A	02-12-1994	NONE	
EP 0001540	A	18-04-1979	SE 407758 B AT 367448 B BE 31 T CA 1145696 A CH 646370 A DE 2857355 A DK 437178 A,B, FI 782976 A,B, FR 2432921 A GB 2041402 A,B JP 54089079 A NL 7815044 A NL 7815044 T SE 7711089 A US 4346175 A	23-04-1979 12-07-1982 31-01-1980 03-05-1983 30-11-1984 22-05-1980 05-04-1979 05-04-1979 07-03-1980 10-09-1980 14-07-1979 31-01-1980 31-01-1980 05-04-1979 24-08-1982
WO 9308694	A	13-05-1993	AT 397811 B AT 219191 A AU 2885992 A DE 59208144 D DK 615409 T EP 0615409 A ES 2101123 T	25-07-1994 15-11-1993 07-06-1993 10-04-1997 01-09-1997 21-09-1994 01-07-1997
GB 2239800	A	17-07-1991	NONE	
US 3486969	A	30-12-1969	SE 309153 B FI 45998 B	10-03-1969 31-07-1972
DD 292864	A		NONE	